



The Alsa Corporation

Product Number
CB-3012

CB-3012
Color Blender
Description
Color Blender

Reducer
AMR-2712

Description
Medium Reducer

Description
CB-3012 Color Blender is intended for use as a tool to blend with Pearls, Candy Concentrates, and Flakes.

Surface Preparation
Old cured finishes must be thoroughly cleaned and sanded in areas where CB-3012 will be applied

Mixing Ratio (1:1)
Mix 1 part CB-3012 to 1 part AMR-2712.

Application
Adjust air pressure at the gun to 35-45 psi for gravity or siphon feed application or 5-7 psi at the cap for HVLP.

Apply 1-2 light to medium coats of the color blender onto the blend area, extending each coat a little further each time. Allow 5-10 minutes between coats.

Dry times at 70° F
Dust Free in Time 10 minutes
Tack Free Time in 15 minutes
Tape Free Time in 45 minutes

Equipment Clean-up
Clean equipment immediately after use with AMR-2712

Technical Data

Viscosity #2 Zahn (RTS)	18-20 sec.
Volume Solids(RTS)	12%
Film Build Per coat	0.5 Mil
Disposal/Safety	See MSDS
Humidity Resistance	Excellent