



**The Alsa Corporation**

## MCC-7125/MCCH-7125 Clearcoat / Hardener

### Product Number

MCC-7125

### Description

Polyurethane Clearcoat

### Hardeners

MCCH-7125

Hardener

### Description

Normal

### Description

MCC-7125 is a acrylic urethane clearcoat.

### Mixing Ratio (4:1)

Mix 4 parts MCC-7125 to 1 part MCCH-7125

### Application

Apply 2-3 wet coats at 25 psi allowing 10-15 minute flash between coats. Keep spray gun 6-10 inches away from the substrate to avoid problems associated with air entrapment.

### Dry times at 77° F

Dust Free in 20 minutes

Tack Free in 30 minutes

### Force Drying

Flash time @ 77° F      15 Minutes

Bake Time @140°F      45 Minutes

Allow 1-2 hours before wet sanding and buffing.