



The Alsa Corporation

The World's Most Exotic Finishes

TECHNICAL DATA SHEET

COLOR BLENDER KCCB3012

ALSA CODE	GPI CODE	DESCRIPTION	SIZE
CB-3012	KCCB3012	Color Blender	Quart
AMR-2712	KCAMR2712	ALSA Medium Urethane Reducer	Pint / Quart

PRODUCT DESCRIPTION

CB-3012 Color Blender is intended for use as a tool to blend with Pearls, Candy Concentrates, and Flakes.

SURFACE PREPARATION

Old cured finishes must be thoroughly cleaned and sanded in areas where CB-3012 will be applied.

MIXING RATIO (1:1)

Mix 1 part CB-3012 to 1 part AMR-2712

APPLICATION

Adjust air pressure at the gun to 35 - 45 PSI for gravity or siphon feed application or 5 - 7 PSI at the cap for HVLP.

Apply 1 - 2 light to medium coats of the color blender onto the blend area, extending each coat a little further each time. Allow 5 - 10 minutes between coats.

DRYING TIMES AT 70° F

Dust Free in Time 10 minutes
Tack Free Time in 15 minutes
Tack Free Time in 45 minutes

EQUIPMENT CLEAN-UP

Clean equipment immediately after use with AMR-2712

TECHNICAL DATA

Viscosity #2 Zahn (RTS)	18 - 20 seconds
Volume Solids (RTS)	12 %
Film Build Per Coat	0.5 Mil
Disposal / Safety	See MSDS
Humidity Resistance	Excellent



GPI AUTOMOTIVE PRODUCTS P/L
MELBOURNE • SYDNEY • BRISBANE • PERTH • ADELAIDE • LAUNCESTON
FREE CALL 1800 334 898

View GPI's range of products at: www.gpi.com.au/autocart then quote our product code to your supplier for delivery.